



NORTH SHORE RUBBER

Technical Data Sheet TDP-B Tire-Derived Polymer Product Code 0494

TDP-B (Tire-Derived Polymer) is a 100% re-engineered rubber masterbatch compound made from truck tires or truck tread. It is a versatile, functional material that offers significantly higher performance to differentiate it from fillers such as crumb rubber, micronized rubber powder, or reclaimed rubber.

TDP-B is intended to be used as a polymer replacement, and can be used to displace virgin rubber, SBR, EPDM, prime or recycled grade polypropylene (PP), high-density polyethylene (HDPE) and nylons.

TDP-B is used in the automotive, industrial, construction and consumer products markets.

Application Examples

New Tires: Tread & Sidewall
Retreaded Tires: Truck & OTR
Conveyor Belts & Material Handling

Typical Loading

15-20%
15-30%
20-45%

Molding Applications

Automotive Parts
Shoe Soles

20-50%
30-70%

Loading levels vary depending on quality requirements and specifications.

Typical Properties:

Properties can be optimized on an individual basis. Changes in processing conditions or cure will result in different properties.

Property	ASTM	Typical Value	Range
Mooney Viscosity (1+4 @ 212F)	D1646	45	+/- 30
Hardness, Shore A	D2240	58	+/- 3
Density, g/cm ³	D297	1.14	+/- 0.03
Physical Properties	D412, 20"/min		
Tensile, psi (MPa)		1450 (10)	+/- 145
Elongation at break, %		270	+/- 30
Stress at 100% strain, psi (MPa)		330 (2.3)	
Tear, lb/in (N/mm)	D624, die C	200 (35)	
Flexometer	D623		
Hysteresis, °C		25	
Blow-out Minutes		3.5	
Abrasion, mm ³	D5963	160	
Schob Rebound, %	D7121	35	

No solvents or chemicals are used in the process of making TDP-B.

Cure:

Typical values are shown produced from IS6306-1971 standard cure package.

Ingredients	Grams
Tire-Derived Polymer (TDP-B)	200
Zinc Oxide	5.0
Stearic Acid	2.0
Sulfur	3.0
2-Mercaptobenzothiazole (MBT)	0.5
Diphenyl guanidine (DPG)	0.2

Composition:

The composition of TDP-B will mirror that of the feedstock used to create it. The typical North American truck tire composition is shown below.

Ingredient	%	Range
Natural Rubber (NR)	37	+/- 3
Synthetic Rubber (SBR)	20	+/- 3
Total Polymer Content	57	+/- 3
Carbon Black	27	+/- 3
Ash	7	+/- 2
Acetone Extract	9	+/- 2

Questions? Contact info@northshorerubber.com

Our technical advice - whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and, therefore, entirely your own responsibility. Should, in spite of this, liability be established for any damage, it will be limited to the value of the goods delivered by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery: info@northshorerubber.com

NORTH SHORE RUBBER

